

TEST CERTIFICATE

FROM :Semitech Materials Company

18,Tanhyeon-Ro, 1beon-Gil, Pyeongtaek-City, Gyeonggi-Do, Korea

TEL: +82-31-611-9889 FAX: +82-31-611-9866

GRADE : DP-50N

Surface coating		None			
Color		Transparency			
Specification	Units	Spec.	Measured Values	Test Methods	
Average	Thickness	μm	-	51.0	Micrometer
Tensile Strength	MD	kgf/mm^2	Min. 15	22	JIS-K-6734
	TD		Min. 10	17.0	
Elongation	MD	%	Min. 80	92	JIS-K-6732
at break	TD		Min. 120	135	
Heat	MD	%	-	0.2	110°C*10min
Shrinkage	TD		-	0.2	
Surface tension	MD	Dyne/cm	-	38	Dyne Pen
	TD		-	38	
Guarantee			6 month		