

# T E S T   C E R T I F I C A T E

FROM :Semitech Materials Company

18,Tanhyeon-Ro, 1beon-Gil, Pyeongtaek-City, Gyeonggi-Do, Korea

TEL: +82-31-611-9889    FAX: +82-31-611-9866

**GRADE : Kraft Paper**

Specification		Units	Value	Test Methods
actual substance		g/cm <sup>3</sup>	100.1	JIS P 8124
Average Thickness		μm	155.0	Micrometer
				JIS P 8118
Density		g/cm <sup>3</sup>	0.65	
Smoothness	MD	sec	7	JIS P 8113
	TD		4	
Tensile Strength	MD	kN/m	7.6	JIS P 8113
	TD		3.2	
Elongation at Break	MD	%	2.0	JIS P 8113
	TD		5.1	
Tensile Strength	MD	mN	1,419	JIS P 8116
	TD		1,699	
Porosity		sec	34	JIS P 8117
Stockigt sizing degree		sec	37	JIS P 8122

TEST CONDITION: temperature 23±1℃, humidity 50±2%