

# TEST CERTIFICATE

FROM :Semitech Materials Company					
18,Tanhyeon-Ro, 1beon-Gil, Pyeongtaek-City, Gyeonggi-Do, Korea					
TEL: +82-31-611-9889 FAX: +82-31-611-9866					
GRADE : DAP-250					
Silicon coating 여부			Non		
Color			Transparency		
Property		Units	Spec.	Measured Values	Test Methods
Average Thickness		μm	250 ±20	248.0	Micrometer Methods
Use Temperature		℃	-	~190	DSC
Glass Transition Temperature		℃	-	80.0	DSC
Melt index		g/10min	-	3.1	ASTM-D1238
Gravity		Kg / m³	-	1.370	ASTM-D1505
Tensile	MD	Kg / cm²	200 이상	553.0	ASTM-D882
Strength	TD		180 이상	565.0	
Elongation	MD	%	180 이상	310	
at Brck	TD			330	
Tearing strength	MD	Kg / cm	-	80	ASTM-D1004
	TD		-	90	